



GEOTEX® 401 is a polypropylene, staple fiber, needle-punched nonwoven geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The fibers are needled to form a stable network that retains dimensional stability relative to each other. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 401 conforms to the property values listed below¹. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP approved for AASHTO standards.

MARV²

| PROPERTY | TEST METHOD | ENGLISH | METRIC |
|----------|-------------|---------|--------|
|----------|-------------|---------|--------|

ORIGIN OF MATERIALS

| | | | |
|----------------------------|--|------|------|
| % U.S. Manufactured Inputs | | 100% | 100% |
| % U.S. Manufactured | | 100% | 100% |

MECHANICAL

| | | | |
|-----------------------|-------------|---------|--------|
| Grab Tensile Strength | ASTM D-4632 | 120 lbs | 534 N |
| Grab Elongation | ASTM D-4632 | 50% | 50% |
| CBR Puncture | ASTM D-6241 | 310 lbs | 1379 N |
| Trapezoidal Tear | ASTM D-4533 | 50 lbs | 222 N |

ENDURANCE

| | | | |
|--------------------------|-------------|-----|-----|
| UV Resistance at 500 hrs | ASTM D-4355 | 70% | 70% |
|--------------------------|-------------|-----|-----|

HYDRAULIC

| | | | |
|--|-------------|-------------------------|---------------------------|
| Apparent Opening Size (AOS) ³ | ASTM D-4751 | 70 US Std. Sieve | 0.212 mm |
| Permittivity | ASTM D-4491 | 1.7 sec ⁻¹ | 1.7 sec ⁻¹ |
| Water Flow Rate | ASTM D-4491 | 140 gpm/ft ² | 5704 l/min/m ² |

| | | |
|------------|------------------|------------------|
| ROLL SIZES | 12.5 ft x 360 ft | 3.81 m x 109.8 m |
| | 15 ft x 360 ft | 4.57 m x 109.8 m |

NOTES:

1. The property values listed above are effective 07/13/2015 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.



TESTED. PROVEN. TRUSTED
www.propexglobal.com

Propex Operating Company, LLC · 1110 Market Street, Suite 300 · Chattanooga, TN 37402
ph 800 621 1273 · ph 423 855 1466

ARMORMAX®, PYRAMAT®, LANDLOK®, X3®, GEOTEX®, PETROMAT®, PETROTAC®, REFLECTEX®, and GRIDPRO® are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.